



Provisional Technical Datasheet

M12RR Polypropylene Homopolymer

Injection Molding

Product Characteristics:

Polysure M12RR is Polypropylene Homopolymer, produced by latest Novolen Technology & Primarily suitable for General Purpose Injection Moulding, Furniture & Housewares applications. M12RR combines exceptional processability with low Cycle Time & excellent product aesthetics.

Recommended Applications:

M12RR is recommended for General Purpose Injection Moulding, Closures, Furniture, Housewares & Compounding.

Typical Properties:

Sr. No.	Properties	Test Method	Units	Values*
1	Melt Flow Index (230°C & 2.16 kg)	ASTM D1238	g/10 min	12
2	Tensile Strength @ Yield (50mm / min)	ASTM D638	MPa	34
3	Tensile Elongation @ Yield (50mm / min)	ASTM D638	%	8
4	Flexural Modulus	ASTM D790	MPa	1550
5	Notch Izod Impact Strength (23°C)	ASTM D256	J/m	30
6	Vicat Softening Point (10N)	ASTM D1525	°C	154
7	Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	95

*All the mechanical properties as per ASTM D638 Type I Injection molded specimen prepared in accordance with ASTM D 4101

Processing Guidelines:

- Barrel Temperature :180 - 280°C
- Mold Temperature : 30 - 40°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50 °C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

Regulatory Requirements:

M12RR is manufactured complying the requirements specified in IS on "Specification for Polypropylene & its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore the Additives added in this grade formulation compiles to the "Positive list of constituents of Polypropylene and its Copolymers in contact with Foodstuff, Pharmaceutical & Drinking water" as laid down under IS 10909. In general the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in