

Provisional Technical Datasheet

M0861S Polysure HDPE

Injection Molding

Product Characteristics:

Polysure M0861S is High Density Polyethylene, produced by Gas Phase – UNIPOL™ PE technology, suitable for Injection Molding process. M0861S resin offers superior dimensional stability of the products with high stiffness, good impact resistance, low warpage and good stackability.

Recommended Applications:

Heavy-duty Crates, Helmets, Industrial products

Typical Properties:

Sr. No.	Property	Test Method	Unit	Value*
1	Melt Flow Index (190oC & 2.16 kg)	ASTM D1238	g/10 min	8
2	Density (23°C)	ASTM D1505	g/cc	0.961
3	Tensile Strength at Yield, Type IV Specimen	ASTM D638 (50 mm / min)	MPa	31
4	Tensile Elongation at Break, Type IV Specimen		%	350
5	Flexural Modulus (1% Secant)	ASTM D790A	MPa	1200
6	Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	75
7	Vicat Softening Point (10N)	ASTM D1525	°C	128
8	Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	75

*All the mechanical properties are tested on injection molded Test Specimen, prepared in accordance with ASTM D4101

Processing Guidelines:

- Barrel Temperature : 190 - 220°C
- Mold Temperature : 20 - 30°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

Regulatory Requirements:

M0861S to be manufactured complying the requirements specified in IS 10146 on “Specification for Polyethylene for its safe in contact with Foodstuff, Pharmaceutical & Drinking water”. Furthermore, the Additives added in this grade formulation compiles to the “Positive list of constituents for Polypropylene, Polyethylene and their Copolymers for its safe use in contact with Foodstuffs & Pharmaceuticals’ as laid down under IS 16738:2018. In general, the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Updated as of May 2021

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above-mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in