

Technical Datasheet

M2024L Polysure LLDPE

Injection Molding

Product Characteristics:

Polysure M2024L is a 1-butene comonomer based Linear Low-Density Polyethylene, produced by Gas Phase – UNIPOL™ PE technology, suitable for Injection Molding & Compounding processes. M2024L offers low warpage, superior dimensional stability for injection molded products & excellent filler dispersibility for masterbatches.

Recommended Applications:

Injection molded Shopping baskets, Lids, Containers, TWIM, Houseware Items, Masterbatches

Typical Properties:

Sr. No.	Property	Test Method	Unit	Value*
1	Melt Flow Index (190°C & 2.16 kg)	ASTM D1238	g/10 min	20.0
2	Density (23°C)	ASTM D1505	g/cc	0.924
3	Tensile Strength at Yield, Type IV Specimen	ASTM D638 (50 mm / min)	MPa	11
4	Tensile Strength at Break, Type IV Specimen		MPa	10
5	Tensile Elongation at Break, Type IV Specimen		%	550
6	Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	500
7	Flexural Modulus (2% Secant)	ASTM D790B	MPa	260
8	Vicat Softening Point (10N)	ASTM D1525	°C	93

*All the mechanical properties are tested on injection molded Test Specimen, prepared in accordance with ASTM D4101

Processing Guidelines:

- Processing Temperature : 180 - 220°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

This grade meets the requirements of IS 7328:2020 - Specification for Polyethylene Material for Moulding and Extrusion.

Regulatory Requirements:

M2024L to be manufactured complying the requirements specified in IS 10146 on "Specification for Polyethylene for its safe in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore, the Additives added in this grade formulation compiles to the "Positive list of constituents for Polypropylene, Polyethylene and their Copolymers for its safe use in contact with Foodstuffs & Pharmaceuticals' as laid down under IS 16738:2018. In general, the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Updated as of July 2025

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above-mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), The Rise, Plot No.17B & 17C, Block – FC, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in