

Technical Datasheet

F0116LM Polysure Metallocene LLDPE

Blown Film

Product Characteristics:

Polysure F0116LM is a 1-hexene comonomer based Linear Low-Density Polyethylene, produced by Gas Phase – UNIPOL™ PE technology, using Metallocene Catalyst and primarily suitable for Multilayer Blown Film Extrusion Process. **This grade contains Slip & Anti-block additives.** Film produced with F0116LM offers smooth processing & superior drawdown characteristic. Film also has outstanding cold temperature, toughness, impact strength and puncture, heat seal strength and optical properties.

Recommended Applications:

High performance multilayer film, Food Packaging film, FFS packaging film, Overwrap film, Heavy duty bags, Barrier film, Freezer Film, Agricultural film, Industrial Packaging, Stand Up Pouches, Lamination Film, Ice bags

Typical Properties:

Sr. No.	Property	Test Method	Unit	Value*
Resin Properties:				
1	Melt Flow Index (190°C & 2.16 kg)	ASTM D1238	g/10 min	1.0
2	Density (23°C)	ASTM D1505	g/cc	0.916
Film Properties*:				
1	Tensile Strength at Yield (MD/TD)	ASTM D882 (500 mm / min)	MPa	10 / 9.5
2	Tensile Strength at Break (MD/TD)		MPa	60 / 60
3	Tensile Elongation at Break (MD/TD)		%	600 / 650
4	Elmendorf Tear Strength (MD/TD)	ASTM D1922	g/micron	10 / 12
5	Dart Impact Strength	ASTM D1709A	g/micron	34
6	Haze	ASTM D1003	%	8
7	Gloss	ASTM D2457, 45°	GU	60
8	Puncture Energy	HMEL Method	J	5.6

* The film properties have been measured on 25.4 µm (1.0 mil) thick films (Blow-up ratio: 2.5, Die Gap: 1.8 mm)

Processing Guidelines:

- Barrel Temperature : 175 - 220°C
- Blow Up Ratio : 2 - 3
- Die Gap : 1.8 - 2.5 mm

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

This grade meets the requirements of IS 7328:2020 - Specification for Polyethylene Material for Moulding and Extrusion.

Regulatory Requirements:

F0116LM to be manufactured complying the requirements specified in IS 10146 on "Specification for Polyethylene for its safe in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore, the Additives added in this grade formulation compiles to the "Positive list of constituents for Polypropylene, Polyethylene and their Copolymers for its safe use in contact with Foodstuffs & Pharmaceuticals' as laid down under IS 16738:2018. In general, the additives & constituents used in the grade are in line with requirements laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Updated as of July 2025

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above-mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), The Rise, Plot No.17B & 17C, Block – FC, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in